

Appl No.: 10/665,339

Atty. Dkt. UCF-397CIP

RECEIVED
CENTRAL FAX CENTER

NOV 29 2006

Amendment to the Claims:

This listing of the claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

Claim 1 (Currently amended). A method of efficiently generating holograms ~~having~~ diffraction efficiency ~~up to approximately 100%~~ from photo-thermo- refractive (PTR) glasses having a diffraction efficiency of at least approximately 20%, comprising the steps of:

providing a PTR glass blank having a total contamination with iron and heavy metals below 5 parts per million;

exposing the PTR glass blank with a UV light source or other source of ionizing radiation to create precursors of nucleation centers which are color centers and ions with changes in valence states;

exposing the UV exposed PTR glass blank containing precursors of nucleation centers with a high-power Visible light source greater than approximately 10 MW/cm² to decrease concentration of the precursors to decrease the rate of crystallization at the development stage ~~thereby increasing~~ to increase a refractive index in the PTR glass after exposure to the visible light to record the hologram, wherein the visible light exposure of the UV exposed PTR glass blank results in partial nonlinear transformation of nucleation centers;

thermal treating the PTR glass exposed to both the UV and high-power Visible radiation to provide phase transformation depending on an amount and a power density of the high-power Visible radiation;

Appl No.: 10/665,339

Atty. Dkt. UCF-397CIP

cooling the thermal treated PTR glass to room temperature to provide refractive index variations according to the amount and the power density of the high-power Visible radiation, wherein a difference between refractive indices in the UV exposed areas and the UV and visible light exposed areas allows hologram recording by visible light radiation; and restoring replaying the hologram from the exposed and thermal treated PTR glass by long wavelength radiation.

Claim 2 (Canceled).

Claim 3 (Currently amended). The method of claim 1 ~~claim 2~~, wherein the step of exposing with UV light source includes a range of approximately 280 to approximately 350 nm.

Claim 4 (Currently amended). The method of claim 1 ~~claim 2~~, wherein the step of exposing with the UV light source is approximately 325nm.

Claim 5 (Currently amended). The method of claim 1 ~~claim 2~~, wherein the step of exposing with Visible light source includes a range of approximately 450 to approximately 600 nm.

Claim 6 (Currently amended). The method of claim 1 ~~claim 2~~, wherein the step of exposing with a Visible light source includes: approximately 532 nm.

Appl No.: 10/665,339

Atty. Dkt. UCF-397CIP

Claim 7 (Original). The method of claim 1, wherein the step of exposing with a Visible light source includes: a high power source generating at approximately 10 megawatts/ cm^2 to approximately 100 gigawatts/ cm^2 .

Claim 8 (Original). The method of claim 7, wherein the high power source generates at approximately 100 megawatts/ cm^2 .

Claim 9 (Original). The method of claim 7, wherein the high power source generates at approximately 10 gigawatts/ cm^2 .

Claim 10 (Original). The method of claim 1, wherein the step of generating a hologram includes the step of:

generating a simple hologram having substantially planar surfaces of equal refractive index.

Claim 11 (Original). The method of claim 1, wherein the step of generating a hologram includes the step of:

generating a complex hologram having substantially curved surfaces of equal refractive index.

Claim 12 (Original). The method of claim 1, wherein the step of thermal treating includes the step of:

Appl No.: 10/665,339

Atty. Dkt. UCF-397CIP

thermal treating the PTR glass in a temperature region ranging from approximately 480 to approximately 580°C for a period of from a few minutes to several hours appropriate for phase transformation.

Claim 13 (Currently amended). A method of generating optical components from photo-thermo-refractive (PTR) glasses, comprising the steps of:

providing a PTR glass blank having a reduced concentration of total contamination with iron and heavy metals ~~below 5 parts per million;~~

exposing the entire PTR glass blank with a UV light having a wavelength within the limits of the UV spectrum to produce color centers;

exposing the UV exposed PTR glass with a high-power Visible light source for optical excitation of the color centers to partially bleach the color centers to record ~~the a~~ phase hologram by refractive index modulation, the partial bleaching being non linear due to the high-power Visible light exposure;

thermal treating the UV and Visible light exposed PTR glass; and

cooling the thermal treated PTR glass to generate a holographic optical component from the thermal treated PTR glass for a visible region.

Claim 14 (Previously presented). The method of claim 13, wherein the cooling step to generate the optical component includes the step of:

generating the optical component from one of a lens or multi-lens objective, a combination of a prism or mirror with lenses, and a divergent/convergent beam splitter/combiner.

Appl No.: 10/665,339

Atty. Dkt. UCF-397CIP

Claim 15 (Currently amended). An apparatus comprising:

a photo sensitive refractive (PTR) glass;

a UV source for exposing the PTR glass to produce a PTR glass having
photosensitivity to visible light caused by the UV exposure to create color centers in the PTR
glass, the PTR glass having ~~a total contamination with iron and heavy metals below 5 parts~~
~~per million;~~

a visible light source for exposing the UV exposed PTR glass to Visible light greater
than approximately 10 MW/cm^2 to increase a refractive index in the PTR glass for non linear
bleaching of the color centers;

means for thermal treating the UV and Visible light treated PTR glass to fabricate a
hologram or a phase plate from the PTR glass for a visible region, the hologram generated by
refractive index modulation ~~having a diffraction efficiency up to approximately 100%; and~~

means for using the PTR glass as one of a refractive and a diffractive volume
holographic optical element based on modulation of a refractive index ~~and an increment of~~
~~refractive index, respectively.~~

Claim 16 (Previously presented). The apparatus of claim 15, wherein the UV exposure
includes a range of approximately 280 nm to approximately 350 nm.

Claim 17 (Previously presented). The apparatus of claim 16, wherein the UV exposure is
approximately 325 nm.

Appl No.: 10/665,339

Atty. Dkt. UCF-397CJP

Claim 18 (Previously presented). The apparatus of claim 15, wherein the Visible light exposure includes a range of approximately 450 nm to approximately 600 nm.

Claim 19 (Previously presented). The apparatus of claim 18, wherein the Visible light exposure is approximately 532 nm.

Claim 20 (Previously presented). The apparatus of claim 15, wherein the thermal treatment means includes a range of approximately 480 to approximately 580°C for a period of from a few minutes to several hours appropriate for phase transformation.

Claim 21 (Previously presented). The apparatus of claim 15, wherein the holographic optical element includes: a simple hologram having substantially planar surfaces of equal refractive index.

Claim 22 (Previously presented). The apparatus of claim 15, wherein the holographic optical element includes: a complex hologram having substantially curved surfaces of equal refractive index.

Claim 23 (Currently amended). A method of generating refractive optical elements from photo-thermo- refractive (PTR) glasses, comprising the steps of:

providing a PTR glass having a total contamination with iron and heavy metals below 5 parts per million;

Appl No.: 10/665,339

Atty. Dkt. UCF-397CIP

exposing PTR glass with a source of UV ~~ionizing~~ radiation for generation of color centers;

exposing the UV exposed PTR glass with a high-power Visible light source for nonlinear partial bleaching of the color centers;

thermal treating the UV and Visible light exposed PTR glass for spatial modulation of a refractive index, wherein after thermal treatment a refractive index in the UV and Visible light exposed area is higher than in a single exposed area and lower than in unexposed areas;
and

~~restoring~~ replaying a hologram ~~having up to approximately 100% diffraction efficiency~~ from the thermal treated PTR glass.

Claim 24 (Original) The method of claim 23 wherein the source of ionizing radiation is a UV light source.

Claim 25 (Previously presented). The method of claim 23, wherein the refractive optical elements are lenses, waveguides, waveguide arrays, a multiplexer, demultiplexer and a combination multiplexer/demultiplexer devices.